

DUROMASTIC P15

MODIFIED ACRYLIC URETHANE MEMBRANE FOR UNDER TILE WATERPROOFING



DESCRIPTION

DURO MASTIC™ P15 is a modified acrylic urethane membrane. It has been formulated to create a tenacious bond to most surfaces. DURO MASTIC™ P15 forms a tough, flexible waterproof membrane with a high film strength and exceptional elongation and elasticity, that will expand and contract under normal substrate movement. It is supplied as a thixotropic liquid, which is easily applied to both vertical and horizontal surfaces. The formulation is fully optimised to ensure quick tackfree time, fast cure, high solids and excellent resistance to swelling. It fully complies with the test requirements of [AS:4858-2004](#) and [AS:3740:2004](#) "Waterproofing of Wet Areas within residential buildings"

FEATURES

- Single component
- Water based
- Excellent water resistance
- High Solids
- Ease of application – brush / roller
- Tenacious bond
- Suitable for most substrates
- High tensile film strength & elongation
- Does not bleed or leach
- Extremely low VOC

USE AREA

- Internal Wet Areas and Shower Recesses
- External Balconies and Decks
- Tanking
- Roofs - topcoat with DURO MASTIC™ AC (UV coating) or AC Non Slip or SR.
- Water Features
- Planter Boxes

PACKAGING

- 15 Litre
- 4 Litre

TECHNICAL INFORMATION

Colour	Grey or Green
Weather Resistance	Good
Dry Time	2-4 hours @ 25°C
Recoat Time	4-6 hours @ 25°C
Floor Coverage	Min. 2 coats, each @ 1.0 litre/ m ² [0.5 litre/ m ²]
Wall Coverage	Min. 2 coats, each @ 0.5 litre/ m ² [0.25 litre/ m ²]
Wet Film Thickness	1.0 mm per coat for floor
Dry Film Thickness	1.2 mm total (Class III)
Elongation	+800% @ 25°C
VOC	9 grams/litre
Solids Content	61% by volume
Shelf Life	12 months in unopened containers @ 20°C



INSTALLATION

SURFACE PREPARATION

Ensure wall and floor lining sheets are firmly fixed to manufacturer's directions. Surfaces must be free of dirt, dust, loose particles, oil, contaminants and curing compounds etc.. Concrete must be a minimum strength of 20MPa and have cured a minimum of 28 days. Surfaces must be dry. Fill all screw holes, cracks and voids with neutral-cure silicone sealant. Install leak control flanges to all pipe penetrations

PRIMING

Prime fibre cement board, sound concrete and block work with DUROTECH ARW internally. For external applications prime with Durotech AR Sealer applied at approx. 6m/li2tre. For surfaces that are difficult to adhere to, damp or subject to rising damp seal with DUROMIX™ Hibuild WBE. Allow primer to dry prior to membrane application. Apply a plumbing PVC primer to all PVC fittings.

DETAILING

Apply a 12mm fillet of neutral cure silicone sealant between all horizontal and vertical junctions such as floor to wall, wall to wall, all hob junctions and any joints in the substrate. Apply neutral cure silicone around penetrations and outlets. Where angles are installed, such as across bathroom doorways or under shower screens (hobless showers), the angle must be firmly adhered. Joints, corners & other details shall be reinforced with polyester bandage which must be fully wetted out without wrinkles or bubbles. Alternatively, Duro Flashing Tape may be used.

APPLICATION

To the primed surfaces, apply DURO MASTICTM P15 by brush or roller in at least two or more coats to achieve a minimum dry film thickness of 1.2 mm on floors and 0.6 mm for walls.

Turn membrane up to walls, penetrations and down into drainage outlets. When dry, check for pinholes and recoat if necessary. If the membrane becomes dirty or damaged between coats, clean with water and recoat. All sheet flooring must be fixed according to the manufacturer's directions before the membrane is applied. Do not apply above 30°C or below 10 o C ambient. In high humidity & coolness, drying will be slowed, therefore increase air flow. Avoid applying coats too thickly in hot windy conditions

FLOOD TEST & TILING

A flood test may be carried out after 72 hours of drying at 25°C and 50% R.H.. Apply water to a depth of 25mm for approximately 2 hours. DURO MASTICTM P15 may be tiled over after 3-4 days at 25°C & 50% R.H., using a quality cement based tile adhesive installed as per AS 3958.1.

CLEANING

DURO MASTICTM P15 may be washed from equipment with water when still wet.

PRECAUTIONS

Refer Durotech MSDS prior to use.

Durotech Industries Pty Ltd

Address 14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone +61 2 9603 1177
Fax +61 2 9475 5059
Email sales@durotechindustries.com.au
Web www.durotechindustries.com.au



DUROTECH INDUSTRIES



"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attachments and suggests that the recipient check this document and any attached files for the presence of viruses."

